

Effect of Sugarcane Bagasse Ash (SCBA) on Compressive Strengthof Concrete

Sunil Kumar¹ and Vaneeta Devi²

^{1,2}Assistant Professor, College of Technology, G.B.Pant University of Agriculture and Technology, Pantnagar, Uttarakhand Corresponding Author: Sunil Kumar

Date of Submission: 01-05-2024

Date of Acceptance: 15-05-2024

ABSTRACT: The main ingradient of Concrete is the Ordinary Portland Cement (OPC). The use of OPC in concrete is increases drastically with the development and growth. Ordinary Portland Cement (OPC) is the main ingredient of conventional concrete and is responsible for a major amount of greenhouse gases such as carbondioxide emission in the atmosphere which causes global warming and environmental pollution. The various forms of modern sustainable concrete use industrial waste, such as fly ash from blast furnaces, silica fume, slag, and rice husk ash, to reduce the amount of greenhouse gases released during the concrete-making process. Sugarcane is major crop grown in over 115 countries and its total production is over 1850 million tons. Sugarcane production in India is over 300 million tonnes per year. The processing of it in sugar-mill generates about 10 million tonnes of sugarcane bagasse ash (SCBA) as a waste material. One tonne of sugarcane can generate approximate 26% of bagasse and 0.62% of residual ash. This research addresses the suitability of sugarcane bagasse ash (SCBA) in concrete used as partial cement replacement. Four grade grades of concrete M15, M20, M25 were used for the experimental analysis. The cement was partially replaced by SCBA at 0%, 5%, and 10%, by weight in normal strength concrete (NSC). The outcome of this work indicates that maximum strength of concrete could be attained at 5% replacement of cement with SCBA. Furthermore, the SCBA also gives compatible slump values which increase the workability of concrete.

KEYWORDS: Workability, Compressive Strength, SCBA

I INTRODUCTION

Concrete is the widely used manmade material on earth. The exponential rise in its use

has coincided with the world population's rapid growth.The concrete sector contributes 5% of all greenhouse gas emissions, which causes climate change worldwide.ased on statistical data, the yearly manufacturing of cement is associated with over 4 billion tons of carbon emissions. In addition, the manufacture of cement has raised the atmospheric concentration of carbon footprints to 380 parts per million, with an anticipated increase to 800 parts per million by the year 2100. These days, the construction industry uses a variety of supplemental cementing materials (SCMs) to minimize the amount of cement required and, in turn, carbon emissions. These SCMs include metakaolin, fly ash, slag, and silica fume, SCBA. Sugarcane is major crop grown in over 115 countries and its total production is over 1850 million tons. Sugarcane production in India is over 300 million tonnes per year. The processing of it in sugar-mill generates about 10 million tonnes of sugarcane bagasse ash (SCBA) as a waste material. One tonne of sugarcane can generate approximate 26% of bagasse and 0.62% of residual ash. The enormous volume of bagasse ash, the leftovers from the in-line sugar business, and the bagassebiomass fuel have all been tried to be used in the electric generation sector. This garbage also produces ash with amorphous silica, which has pozzolanic qualities, when burned under controlled settings. A few studies have been conducted on ashes that are directly taken from the industries to investigate their potential as binders that can partially replace cement and their pozzolanic activity. It is also utilized in concrete without compromising the material's durability. As a result, it is feasible to replace cement with Sugarcane Bagasse Ash (SCBA) to increase concrete's qualities, lower its cost of building, and enhance its features.



II METHODOLOGY

In this study waste materials used are sugarcane bagasse ash. The sugarcane bagasse ash is used to replace ordinary Portland cement by 5%, 10%, 15% every mixes that are prepared. These concrete mixes are prepared for M15 to M25 grade of concrete. For each grade replacement of mix concrete samples are made and nominal Mix is also made to compare the results. The Samples are prepared and tested for 7 Days and 28 Days Compressive Strength Tests.

III. MATERIAL USED FOR THE RESEARCH

3.1.1 Cement. The ordinary Portland cement (Grade 43) was used in this research to prepare the control specimens.

3.1.2 Fine aggregate. Fine aggregate (commonly known as hill sand) free from debris were brought from nearby having 2.61 of specific gravity and size below 4.75 mm were used.

3.1.3 Coarse aggregate. Coarse aggregate commonly known as crushed aggregates were also bfrom nearby having 2.65 of specific gravity and nominal maximum size of 20 mm were used.

3.1.4 Water. Water (palatable liquid) accessible within the campus laboratory were utilized for the mixing and curing of concrete cubes .

3.1.5 Sugarcane bagasse ash. Sugarcane bagasse brought from vicinity of Pantnagar and was burnt in a closed drum (uncontrolled burning), SCBA was obtained after passing through 300µm standard sieve used for experimental study.

 Table 1. Typical chemical composition of Sugarcane bagasse ash

Sugarcane Dagasse ash			
S. No.	Component	Percentage	
1	Sio ₂	60-65	
2	Al ₂ O ₃	3-5	
3	Fe ₂ O ₃	6-10	
4	CaO	9-12	
5	MgO	1-3	
6	SO ₃	1-2	
7	K ₂ O	2-6	
8	LOI	3-5	

IV EXPERIMENTAL PROGRAM

1. The Mix design was done for the M15-M30. The Cubes were casted for M15-M30 grade of concrete for

2. In a pan take the weighted materials i.e. fine aggregate (sand), coarse aggregate, cement and sugarcane bagasse ash as in ratio found for mix design.

3. Mix the materials in dry state thoroughly.

4. Dry mix all the materials. After thoroughly mixing the materials make a hollow as crater in the Centre.

5. Start adding water in the mix at small amount at a time and start mixing them, water should be added as per the water cement ration taken in mix design.

6. After concrete is mixed start placing it in oil polished Cube molds up to 1 / 3 of its part. Now after this start temping the placed mixture in mould for 25 times, fill the mould up to 2 / 3 and repeat the temping process.

7. Now completely fill the mould and temping it for 25 times in last portion, level it then put on Table Vibrator for compaction.

8. Then keep for 24 hours. After 24 hours take the specimen out of the moulds and keep for Curing in curing tanks.

9. After 7 & 28 Days take out the specimens of curing tanks and leave them for some time to surface dry them. After this perform the Compressive Strength tests.

V RESULTS & DISCUSSION

Workability :

The slump test was performed for the concrete with and without SCBA to check the consistency concrete and the observed result are reported in table 2.After the conducting slump test for concrete grade M15, M20 and M25 the continuous rise in the slump value were recorded, when cement replaced by SCBA. It is prominent that slump value represents the workability of fresh mix concrete and the observed values fall in the category of low and medium degree of workability.

Table 2.Slum	values	of differen	t grades	of
--------------	--------	-------------	----------	----

concrete.			
Mix	%	Average	
	Replacement	Slump Value	
	SCBA	(mm)	
	0	32	
M15	5	38	
	10	45	
	15	55	
M20	0	30	
	5	42	
	10	51	
	15	60	
M25	0	70	
	5	85	
10123	10	90	
	15	100	

DOI: 10.35629/5252-030516341637 Impact Factor value 7.429 | ISO 9001: 2008 Certified Journal Page 1635





Fig1 Av. Slump values (in mm) for different grade corresponding to various % of SCBA

Compressive Strength:

The compressive testing machine was used to test the entire concrete cylinders for crushing strength at 7 and 28 days respectively. The compressive strength for concrete grade M15, M20 and M25 (1:2:4) were investigated for the control mix and while cement was partially replaced by SCBA. The results of compressive strength test at 7 days and 28 days curing periods are provided in table 3 and 4. Through the laboratory observations it was perceived that early age strength is lower than the later age strength, because concrete gain its strength with the passage of time.

It can be seen that the use of SGBA as partial replacement of cement increases the compressive strength of concrete by a significant amount. The compressive strength of concrete can be increased upto 10% of replacement of cement after which there is a fall in compressive strength with further increase in SGBA content. Thus, the optimum content of SGBA is 10%

		U	~
Mix	Av.	Av.	Av.
	Comp.	Comp.	Comp.
	Strength	Strength	Strength
	(MPa)	(MPa)	(MPa)
	for M15	for M20	for M25
Cement +	12.12	16.23	19.23
0% SCBA			
Cement +	13.23	17.25	20.12
5% SCBA			
Cement +	14.25	18.66	22.56
10% SCBA			
Cement +	13.23	16.89	20.28

 Table 3 Compressive Strength at 7 days





Table 4 Compressive Strength at 28 days

		0	
Mix	Av.	Av.	Av.
	Comp.	Comp.	Comp.
	Strength	Strength	Strength
	(MPa)	(MPa)	(MPa) for
	for M15	for M20	M25
Cement +	20.58	28.33	32.33
0% SCBA			
Cement +	22.36	29.12	34.26
5% SCBA			
Cement +	23.26	30.12	37.85
10%			
SCBA			
Cement +	22.35	28.35	36.56
15%			
SCBA			



Fig 2 Av. Compressive strength (MPa) for different grade corresponding to various % of SCBA for 28 days

DOI: 10.35629/5252-030516341637 Impact Factor value 7.429 | ISO 9001: 2008 Certified Journal Page 1636



VI. CONCLUSION

This work was successfully carried out, to the establishment of SCBA as an alternative cement replacement material in concrete. After the detailed investigation the following conclusions have been

drawn:

- Partial replacement of cement by SCBA boosts workability of fresh concrete; therefore use of super plasticizer is not essential.
- The results showed that, the concrete with 10% SCBA replacement after 28 days of curing, showed maximum strength when compared to concrete with other percentage replacement mixes.
- In the economic point of view, the cement replaced by SCBA saves money
- The usage of SCBA in concrete is not only a waste-minimizing technique, also it saves the amount of cement.

REFERENCES

- A. Bahurudeen and M. Santhanam, "Sugarcane bagasse ash - An alternative supplementary cementitious material", Proc., International Conference on Advances in Civil Engineering and Chemistry of Innovative Materials, SRM University, Chennai, India, pp. 837–842, 2014.
- [2]. Andrade, "Calculation of chloride diffusion coefficients in concrete from ionic migration measurements", Cement and Concrete Research, Vol. 23, Issue 3, pp.724-742, 1993.
- [3]. Cordeiro, E. Vazquez, Ch.F. Hendricks and G.M.T. Janssen, "Influence of mechanical grinding on the pozzolanic activity of residual sugarcane bagasse ash", Proc., International RILEM conference on the use of recycled materials in building structures, 2004.
- [4]. G.C. Cordeiro, R.D. Filho, L.M. Tavares and E.M. Fairbairn, "Effect of calcination temperature on the pozzolanic activity of sugar cane bagasse ash", Construction and Building Materials, Vol. 23, Issue 10, pp. 3301-3303, 2009a.
- [5]. G.C. Cordeiro, R.D. Filho, L.M. Tavares and E.M.Fairbairn, "Ultrafine grinding of sugar cane bagasse ash for application as pozzolanic admixture in concrete", Cement and Concrete Research, Vol. 39, Issue 2, pp. 110-115, 2009b.

- [6]. G.C. Cordeiro, R.D. Filho, L.M. Tavares and E.M. Fairbairn, "Ultrafine grinding of sugar cane bagasse ash for application as pozzolanic admixture in concrete", Cement and Concrete Research, Vol. 39, Issue 2, pp. 110-115, 2009b.
- [7]. J.L Escalante-Garcia and J.H Sharp, "The microstructure and mechanical properties of blended cements hydrated at various temperatures", Cement and Concrete Research, Vol. 31, Issue 5, pp. 695-702, 2001.
- [8]. J. Payá, J. Monzó, M.V. Borrachero, L. Díaz-Pinzón, L.M. Ordónez, "Sugar-cane bagasse ash (SCBA): studies on its properties for reusing in concrete production", Journal of chemical technology and biotechnology, Vol. 77, Issue 1, pp. 321-325, 2002.
- [9]. K. Ganesan, K. Rajagopal and K. Thangavel, "Evaluation of bagasse ash as supplementary cementitious material", Cement and Concrete Composites, Vol. 29, pp. 515–524, 2007.
- [10]. M. Frias, V. Ernesto and S. Holmer, "Brazilian sugar cane bagasse ashes from the cogeneration industry as active pozzolans for cement manufacture", Cement and Concrete Composites, Vol. 33, Issue 4, pp. 490-496, 2011.

DOI: 10.35629/5252-030516341637 Impact Factor value 7.429 | ISO 9001: 2008 Certified Journal Page 1637